

# THERMOBREAK<sup>TM</sup> tube

Thermal Insulation

Hot & Cold Pipe Insulation



- BS 476 Class "0"
- AS 1530.3
- ISO 5659-2
- UL94
- NFPA 90A & NFPA 90B



## SEKISUI

**FOAM**  
INTERNATIONAL  
Global Foam Solutions

**Australian Plant:**  
1-5 Parraweena Rd, Taren Point NSW 2229 Australia  
PO BOX 2898, Taren Point NSW 2229 Australia  
[www.sekisuijilon.com.au](http://www.sekisuijilon.com.au)  
[info@sekisuijilon.com.au](mailto:info@sekisuijilon.com.au)

**Thailand Plant:**  
700/329 Moo 6, Amata Nakorn Industrial Estate,  
Tumbol Donhua-loh, Amphur Muang Chonburi 20000  
Thailand  
[info@thaisekisui.co.th](mailto:info@thaisekisui.co.th)

RU is a registered trademark of United Laboratories Inc.  
Thermobreak is a trademark of Sekisui Chemical Co. Ltd.

- > Completely closed cell, physically cross-linked foam pipe insulation.
- > Heat bonded factory applied reinforced aluminium foil.
- > Pre-slit for faster installation.
- > Flexible, tough and durable.
- > Excellent compression resistance due to it's crosslinked foam structure.
- > Superior insulating properties compared to other flexible closed cell foams.
- > Very high vapour diffusion resistance Class 1 Vapour Retarder under ASHRAE 2009.
- > No cladding required.
- > Conforms to ISO 5659-2 "Smoke Density and Toxicity".
- > UL Recognised Component.
- > Anti-Microbial.
- > Can be used outdoors.
- > Certified Green Star Product (VOC)
- > Complies to NFPA 90A & NFPA 90B

## Size Availability

Wall thickness (mm)	Min ID (mm)	Max ID (mm)	IPS Max (in)
15 mm	9.5	273.0	10"
20 mm	7.0	219.2	8"
25 mm	7.0	219.2	8"
30 mm / 35 mm	9.5	219.2	8"
40 mm / 50 mm	12.7	168.3	6"

**Tube length: 2 metres**

(Other lengths available on request)

## Technical Data

Material:	Irradiation (physically) crosslinked polyolefin foam with factory applied reinforced foil.
Density:	25kg/m <sup>3</sup> (foam core only)
Thermal Conductivity: (ISO 8302-1991)	0.032 W/mK (@ 23°C mean temperature)
Water Vapour Permeability: (ASTM E96)	8.19 X 10 <sup>-15</sup> kg/Pa.sm (0.29 mg.m/Nh)
Water Vapour Permeance:	3.3 X 10 <sup>-4</sup> g/M.N.s
Permeability resistance factor:	μ>20,000
Water absorption by volume:	0.8% (after 28 days)
Resistance to Fungi: (ASTM G21)	Zero Growth
Ozone Resistance:	Excellent
UV Resistance:	Excellent
Operating temperature:	-80°C to 100°C

## Fire and Smoke Behaviour

BS 476 Part 6 & 7	Class 0
AS 1530.3 (1999)	
Spread of Flame Index:	0
Heat Evolved Index:	0
Ignitability Index:	0
Smoke Develop Index:	0-1
UL94:	HF-1
ASTME 84:	Complies to: Flame speed index <25 Smoke Index <50
NFPA 90A & NFPA 90B	Complies with requirements
ISO 5659-2 (1994)	Smoke Density & Toxicity (with gas analysis)
Smoke Density:	Dm < 200
Smoke Toxicity:	Satisfies max allowable concentrations for the following combustion gases CO, HCL, HBr, HF, HCN, NOx, SO2
BS 6853 (Smoke density toxicity)	R = 0.66 (satisfies combustion gases to IDLH values)